

COTTON VARIETIES DEVELOPED BY THE PCCC FROM 1985 TO 2017

No.	Variety	Year of Release	Lint %	Staple length (mm)	Micronaire (ug inch-1)	Strength (tppsi)
1	SLH-41	1985	36.0	26.4	4.4	95.8
2	CIM-70	1986	31.5	29.0	4.2	92.5
3	Shaheen(Non-Bt)	1988	27.0	26.9	4.2	-
4	CIM-109	1990	37.5	27.3	4.4	91.0
5	CIM-240	1992	36.5	27.5	4.7	93.7
6	BH-36	1992	38.7	28.0	4.3	100.3
7	CRIS-9	1993	34.5	26.5	-	97.0
8	SLS-1	1995	38.0	27.5	4.4	-
9	CIM-1100	1996	38.0	29.0	3.9	94.0
10	CIM-448	1996	38.0	28.5	4.5	93.8
11	CIM-443	1998	36.7	27.6	4.9	96.0
12	CIM-446	1998	36.2	27.0	4.7	97.4
13	CIM-482	2000	39.2	28.5	4.5	98.0
14	BH-118	2000	38.7	27.6	4.6	96.2
15	Marvi CRIS-5A	2001	35.5	26.8	-	97.5
16	CIM-473	2002	39.7	29.6	4.3	95.2
17	CIM-499	2003	40.2	29.6	4.4	97.3
18	CIM-707	2004	38.1	32.2	4.2	97.5
19	CIM-506	2004	38.5	28.7	4.5	98.9
20	CRIS-134	2004	36.5	27.5	-	97.5
21	CRIS-467	2004	37.0	27.5	4.6	97.2
22	CIM-496	2005	41.1	29.7	4.6	93.5
23	CIM-534	2006	40.1	29.0	4.5	97.2
24	CRIS-121	2006	36.8	27.5	4.9	98.5
25	CIM-554	2009	41.5	28.5	4.7	96.8
26	CIRS-342	2010	38.5	28.4	4.3	95.5
27	CIM-573	2012	39.3	31.6	4.7	92.5
28	Bt CIM-598	2012	41.8	29.0	4.3	94.8
29	BH-167	2012	41.1	29.1	4.7	92.7
30	SLH-317	2012	38.0	29.8	4.4	96.7
31	Bt CIM-595	2013	39.5	29.0	4.7	97.5
32	Bt CIM-599	2013	40.3	30.2	4.6	96.3
33	Bt CIM-602	2013	38.0	29.5	4.8	95.0
34	CIM-608	2013	41.1	28.5	4.6	93.9
35	CRIS-129	2014	38.5	28.5	-	98.5
36	Bt CIM-600	2017	40.3	29.0	4.7	94.8
37	Bt Cyto-177	2017	40.0	29.0	4.3	99.9
38	Cyto-124	2015	42.6	30.3	4.4	92.4
39	CIM-620	2016	40.2	28.9	4.6	93.0
40	SLH-8*	2016	39.0	29.0	4.6	-
41	CRIS - 533	2017	40.5	28.8	4.0	97.8
42	CRIS – 510	2017	39.0	28.2	4.0	92.8
43	BT-CRIS - 508	2017	40.5	28.7	4.7	99.4
44	CIM – 598	2017	40.0	29.5	4.6	96
45	CYTO – 179	2017	40.2	28.2	4.2	107.6